

METAL REMOVAL FLUIDS

QUAKERCOOL® 7350 BFF METALWORKING WATER SOLUBLE COOLANT BORON FREE

APPLICATION SHEET

BENEFITS

- » Formaldehyde, boron and secondary amine free
- » Wide range of water hardness
- » Very high emulsion stability even at high hardness
- » Good bio-resistance
- » Good tramp oil rejection
- » Provides good cleanliness on tools/machines and detergency characteristics

APPLICATIONS

High performance micro-emulsion ideally suited to all operations where high surface finish quality and high lubrication is needed. Ideal for general purpose machining of most engineering materials

Recommended for light to medium metalworking operations on cast iron, steel and aluminium

Concentration range:
6 - 10 % depending on type of operation

Make up water hardness:
90 - 500 ppm (9 - 50 °TH, 5 - 28 °DH)

FLUID MAINTENANCE

Poor or incorrect emulsion preparation may lead to instability and could considerably shorten the life of the emulsion. Prior to making any fresh fill, we highly recommend full cleaning including the use of a compatible systems cleaner of all system components which will be in contact with the emulsion. A wide range of system cleaners* and disinfecting additives* are available from Quaker.

*Please consult a Quaker representative for any additional information.



QUAKERCOOL® 7350 BFF

METALWORKING WATER SOLUBLE COOLANT BORON FREE

APPLICATION SHEET

STORAGE/PACKAGING

Quaker Chemical can supply this quality product in drums, in containers and in bulk. Other packages can be made available by Quaker Chemical or by distributors upon request.

As with all metalworking products, QUAKERCOOL® 7350 BFF should be stored in dry conditions and protected from extreme temperatures: 4 - 35 °C is the recommended storage temperature.

QUAKERCOOL® 7350 BFF is unlikely to present any significant health or safety hazard when used as recommended by Quaker. Good standards of personal and industrial hygiene are to be maintained by the user (see Material Safety Data Sheets).

OPERATIONS

Turning	●
Milling	●
Drilling	●
Deep hole drilling	○
Tapping-Threading	●
Reaming	○
Broaching	
Sawing	●
Grinding	○
Honing-Lapping	○

MATERIALS

Cast-iron	●
Steel	●
High alloy steel	●
Stainless steel	●
Aluminium alloys	●
Aero Aluminium alloys	●
Copper alloys	○
Titanium	●
Carbide tool	

● Main application ○ Possible application

PROPERTIES

PROPERTY	TYPICAL VALUE	UNIT
Appearance / Colour	Clear Amber	[-]
Viscosity	65	[mm ² /s @ 40 °C]
Density	1000	[kg/m ³ @ 15 °C]
Pour point	<4	[°C]
Appearance diluted	Opaque	[-]
pH diluted	9,4	[-]
Corrosion threshold	3,5	[% DIN 51360 T2]
Alkalinity factor (pH=5)	2,7	[ml 0,1N/%/ 25 ml]
Acid split factor	0,50	[ml/%]
Refractometer factor	1,3	[%/° Brix]

These characteristics are typical of current production and can't be used as a specification.

quakerchem.com | +31 297 544 644

Prior to using this product, consult the Material Safety Data Sheet for instructions regarding safe handling and environmental issues.

The information contained herein is based on data available to us and is believed to be accurate. HOWEVER, NO WARRANTY OF MERCHANTABILITY, FITNESS FOR ANY USE, OR ANY OTHER WARRANTY IS EXPRESSED OR TO BE IMPLIED, REGARDING THE ACCURACY OF THESE DATA. THE RESULTS TO BE OBTAINED FROM THE USE THEREOF, OR THE HAZARDS CONNECTED WITH THE USE OF THE PRODUCT. Quaker Chemical Corporation assumes no liability for any alleged ineffectiveness of the product or any injury or damage, direct or consequential, resulting from the use of this product unless such injury or damage is solely attributable to negligence on the part of Quaker Chemical Corporation